

**S.C. GRANTMETAL S.A.**

Strada Mehădiei, nr.41, Sector 6, Bucuresti, 060541

Tel.: + 40 (21) 220 55 07, + 40 (21) 220 31 10 | Fax: + 40 (21) 220 94 51

Email: office@grantmetal.ro

**Compozitia chimica (%)**

Marca	Werkstoff	Compozitia chimica (%)						
		C	Mn	Si	P (max.)	S (max.)	Cr	Mo
OLT35		0,09÷0,16	0,40÷0,80	0,17÷0,37	0.04	0.045		
OLT45		0,17÷0,24	0,45÷0,80	0,17÷0,37	0.04	0.045		
P195GH	1.0348	0.13	≤ 0,70	≤ 0,35	0.025	0.02	≤ 0,30	≤ 0,008
P235GH	1.0345	0.16	≤ 1,20	≤ 0,35	0.025	0.02	≤ 0,30	≤ 0,008
P265GH	1.0425	0.20	≤ 1,40	≤ 0,40	0.025	0.02	≤ 0,30	≤ 0,008
E235	1.0308	0.17	≤ 1,20	≤ 0,35	0.03	0.035		
E275	1.0225	0.21	≤ 1,40	≤ 0,35	0.03	0.035		
E355	1.0580	0.22	≤ 1,60	≤ 0,55	0.03	0.035		
16Mo3	1.5415	0,12÷0,20	0,12÷0,20	≤ 0,35	0.025	0.02	≤ 0,30	0,25÷0,35