



S.C. GRANTMETAL S.A.

Strada Mehadiei, nr.41, Sector 6, Bucuresti, 060541

Tel.: + 40 (21) 220 55 07, + 40 (21) 220 31 10 | Fax: + 40 (21) 220 94 51

Email: office@grantmetal.ro

Marca de oțel	Echivalențe			Compoziția chimică (%)								
	DIN	ASTM	Werkstoff	C max.	Si max	Mn max	P max.	S max.	Cr	Al	Ni	Altele
Cr 20 Al 5	Cr Al 20.5	B 603	1.4767	0.1	1.0	1.0	0.04	0.02	19-22	4-5.5	max.0.5	Cu=max.0.5 Fe= rest
Ni40Cr20Fe	X12NiCr36.18	-	1.4863	0.15	1.5-3.5	0.15	0.035	0.03	18-22	max.0.1	35-40	Cu=max.0.5 Fe=rest
Ni60Cr15Fe	-	-	2.4867	0.15	0.5-2	2.0	0.02	0.015	14-19	max.0.1	min.59	Cu=max.0.5 Fe=19-25
Ni 80 Cr 20	NiCr80.20	B 344	2.4869	0.15	0.5-2	2.0	0.02	0.015	19-21	max.0.1	min.75	Cu=max.0.5 Fe=max.1